

AFCONA – 4009E



Chemical Composition

Modified polyurethane polymer, with caprolactone

Product general description

Polymeric dispersant for deflocculation of pigments

Product Properties

AFCONA-4009E is a polymeric dispersant mainly for stabilizing inorganic and some organic pigments. The main advantage of AFCONA – 4009E is the very wide compatibility. It is compatible with long, medium and short oil alkyds, NC, polyurethanes, certain thermoplastic acrylics, epoxy and all the resins for baking paint. Therefore, AFCONA – 4009E is compatible with most of all solvent-based systems.

Compared to other AFCONA PU grade dispersants the viscosity reduction property of AFCONA – 4009E is not too strong, this is due to the more polar structure. However, this is not necessary a disadvantages, because not all mill bases need good viscosity reduction.

The special properties and recommended systems of AFCONA – 4009E :

- 1) Due to its particularly good combination of price and performance, AFCONA – 4009E is a very attractive product to substitute conventional wetting and dispersing agents in all kind of coating systems
- 2) AFCONA – 4009E can be used as post adding additive to correct flooding and floating in all solvent-based paints. If used in mill bases as co-grinding dispersant, the anti-flooding and floating property is also good.
- 3) The pigment concentrate based on AFCONA – 4009E give very unique properties like:
 - not easy dry up
 - very wide compatibility
 - economic

Note: AFCONA – 4009E will become slightly hazy at temperature 5°C and below, but this will not influent the quality.

Product specification

Active ingredients	58 – 61%
Solvents	Butylacetate / Methoxy Propyl Acetate/ Isobutanol
Density at 20 °C	1.00 - 1.02 g/cm ³
Amine value	8 - 15 mg KOH/g
Acid value	10 - 17 mg KOH/g
Flashpoint	24°C
Colour	max.5

Addition and dosage

Calculation method for the required amount of active ingredient of dispersant on pigment:

TiO ₂	: 2 – 3%
Other inorganic pigments	: 2 – 5%
Organic pigments	: 20 – 40%
Carbon blacks	: 20 – 50%

Incorporation

AFCONA-4009E should be incorporated in the mill base before adding the pigments.

Storage

AFCONA-4009E should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container

Packaging

25 kg and 190 kg non-returnable containers