

AFCONA – 4050E



Chemical Composition

Modified polyurethane polymer

Product general description

High molecular weight polymeric dispersant for deflocculation of all type of pigments

Product Properties

AFCONA-4050E is an effective polymeric dispersant for stabilizing inorganic and organic pigments as well as carbon blacks. It has very good stability performance, through effective steric hindrance, on all type of pigments.

This results in:

- improved gloss and DOI
- reduced flooding problems
- higher colour strength
- lower viscosity

AFCONA-4050E was developed for more cost saving purposes without losing too much in pigment stabilizing performance comparing to AFCONA – 4046E.

AFCONA – 4050E has below special properties and recommended in below systems:

- 1) AFCONA – 4050E is used in general industrial where quality requirements are not so high as in OEM and Coil Coating. Thus, it mainly is used in Polyurethane, Epoxy, NC, and general industrial baking paints.
- 2) Although we have mentioned that this product is for cost saving purposes, it performs quite close to the high quality dispersants, such as AFCONA – 4046E and AFCONA – 4047E.
- 3) AFCONA – 4050E also can be used as dispersant in preparation of universal pigment concentrates. We recommend a combination with the universal resin, AFCONA – 1102.

Note: AFCONA – 4050E will become slightly hazy at temperatures below 5° C. This will not influence the quality.

Product specification

Active ingredients	43 – 47%
Solvents	Butylacetate / Methoxy Propyl Acetate / Isobutanol
Density at 20 °C	0.975 – 0.995 g/cm ³
Amine value	10 - 25 mg KOH/g
Flashpoint	24°C
Colour	max.10

Addition and dosage

Calculation method for the required amount of active ingredient on pigment:

TiO ₂	: 2 - 3%
Other inorganic pigments	: 2 - 4%
Organic pigments	: 20 - 40%
Carbon blacks	: 20 - 60%

Incorporation

AFCONA-4050E should be incorporated in the mill base before adding the pigments.

Storage

AFCONA-4050E should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

25 kg and 190 kg non-returnable containers