AFCONA – 5280

Chemical Composition

Cationic/anionic co-polymer with pigment affinity groups

Product general description

Wetting and dispersing additive for solventbased paints

Product Properties

AFCONA - 5280 is in overall the best conventional wetting and dispersing additive. It is economical and still gives very good performance in pigment stabilizing. The performance of AFCONA – 5280 is close to high molecular weight dispersing agents.

AFCONA – 5280 has below special properties and recommended in below systems:

- Very good performance in alkyd based systems like NC, stoving paint and airdrying alkyd.
- 2) Suitable for oil and solvent-based printing inks. It has very good alcohol solubility.
- 3) A good co-grinding agent for all solventbased system.
- Combined with the universal resin AFCONA – 1102 recommended for the preparation of universal pigment concentrates. These pigment concentrates have below advantages:
 - Easy incorporation (even by hand stirring) in NC, thermoplastic acrylic, CAB and polyurethane
 - Economical, because AFCONA 5280 is supplied in nearly 100% active ingredient version
 - Good pigment stability for most pigments, even with PV23

Note: AFCONA – 5280 will become slightly hazy at temperatures below 5° C. This will not influence the quality.

Product specification

Active ingredients $\geq 96\%$

Density at 20 °C	$0.95 - 1.05 \text{ g/cm}^3$
Acid value	25 – 40 mg KOH/g
Amine value	20 – 35 mg KOH/g
Colour	max. 18
Appearance	dark brown liquid

Addition and dosage

0.5 - 1.5% based on TiO_2 or extenders

- 3.0 5.0% based on other inorganic pigments
- 10 30% based on organic pigment.

Incorporation

AFCONA - 5280 should be added prior to the pigment dispersion process.

Storage

AFCONA - 5280 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

25 kg and 200 kg non-returnable containers

AFCONA ADDITIVES SDN BHD (711366-U)

10, Jalan Anggerik Mokara, 31/63, Kota Kemuning, 40460, Shah Alam, Selangor, Malaysia. Tel : +603-5122 2289 Fax : +603-5122 8289 Web Site : www.afcona.com / www.afcona.com.my This datasheet is intended to give technical guidance without any obligation